

PolyCera[®] Titan 70 Ultrafiltration Flat Sheet Membrane Specifications

Membrane Material	PolyCera Titan
Support Non-woven material	Polypropylene
DI Water Permeability* (lmh/bar)	≥200
MWCO (Dalton)	70,000
Nominal Pore Size (nm)	5
Membrane thickness (mm)	0.24
Max Operating Temp (°C)	5 – 70
Max cleaning temperature** (°C)	85 at 2.0 < pH < 10.0 50 at pH > 10.0
Operating pH range	1.0 – 13.5
Free chlorine (mg/l) continuous/instantaneous	≤ 2/50
Total chlorine exposure (ppm.hr)	≤ 100,000
Maximum free oil tolerance (mg/l)	≤ 500
Ozone/peroxide	None

*18mΩ deionized water, pH 7, 20 °C, 1.3 bar

**Cleaning duration of 30 minutes

Note: Prior to use, soak dry membrane for 24 hours with DI water, replace the soaking water every 12 hours.

PolyCera, Inc

721 S Glasgow Ave. Unit D, Inglewood, CA 90301
+1 424.331.7700 | info@polyceramembranes.com
www.polyceramembranes.com